

## Product Data Sheet

<b>Product Reference:</b>	<b>LDPE JAZZ</b>
<b>Description:</b>	Reclaim blown Mixed colour, repelletised polythene, using selected post-industrial LDPE film, filtration of 110-130 is employed in the manufacturing process of the pellets.
<b>Composition:</b>	LDPE coloured blends
<b>Colour / Appearance:</b>	Mixed coloured pellets
<b>Density:</b>	0.920- 0.935 g/cm <sup>3</sup>
<b>Melt Index (2.16/190°C):</b>	0.3-0.9g/10 minutes
<b>Food Contact Regulations:</b>	<b>LDPE JAZZ</b> is not suitable for use in direct food contact applications
<b>Environmental Regulations:</b>	All components used in the manufacture of this product are made from film produced from polymers that meet the requirements as detailed in the packaging (essential requirements) regulations 2015 (implementing 94/62/EC and subsequent amendments), specifically sections 6-12 relating to concentrations of heavy metals.
<b>Storage:</b>	Granules must be stored in dry conditions away from direct sunlight and between 10°C and 25°C.
<b>Health and Safety:</b>	A separate H&S data sheet which includes information on storage, handling and disposal of all YS Reclamation products is available on request.

